

Oppboga Albus™

Virgin fibre board, triple coated on both sides

SUB-STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m ²	µm pt	MD	CD	MD	CD
450	570 23	925 430	45	21		
480	600 24	1150 540	56	26		
540	700 28	1625 800	78	39		
590	800 32	2100 1150	101	56		
640	900 36	2600 1375	126	66		
690	1000 39	3200 1750	155	85		



Engineered to convert like an SBS. Agile. Lean.

APPLICATIONS

For high-end packaging and graphical applications that demand complex designs in terms of graphics and structure.

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	±5%
Thickness (DIN ISO 534)	±5%
Bending stiffness (ISO 5629)	-15%
Surface smoothness (ISO 8791-4)	max. 1.5µm
CIE Whiteness D65/10° (ISO 11475)	min. 120

Printing Surface Properties

ISO Brightness C/2° (ISO 2470)	99
CIE Whiteness.....	125
Surface smoothness (PPS)	1.0µm



The mark of responsible forestry
FSC® C016680