

Oppboga Prominent™

Virgin fibre board, triple coated on both sides

SUB- STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m ²	µm pt	MD	CD	MD	CD
370	570	22	725	320	35	16
400	620	24	900	475	43	23
450	680	27	1125	575	54	28
500	800	32	1725	825	83	40



Superbly printable. Bulky. Lightweight.

APPLICATIONS

Premium packaging for confectionary, beverage, electronics and medical goods • high-end graphical applications (gift cards etc.)

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)±10%
 Thickness (DIN ISO 534)±10%
 Bending stiffness (ISO 5629)-15%
 Surface smoothness (ISO 8791-4)max. 1.7µm
 Brightness C/2° (ISO 2470)min. 87

Printing Surface Properties

ISO Brightness90
 CIE Whiteness D65/10° (ISO 11475)120
 Surface smoothness (PPS)1.0µm
 Gloss 75° (ISO 8254-1)45%