

Oppboga Prominent™

Virgin fibre board, triple coated on both sides

SUB-STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m ²	µm pt	MD	CD	MD	CD
370	560	22	760	330	37	16
400	620	24	900	475	44	23
450	680	27	1125	575	55	28
500	800	31	1725	825	84	40



Superbly printable. Bulky. Lightweight.

APPLICATIONS

Premium packaging for confectionary, beverage, electronics and medical goods • high-end graphical applications (gift cards etc.)

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	±10%
Thickness (DIN ISO 534)	±10%
Bending stiffness (ISO 5629)	-15%
Surface smoothness (ISO 8791-4)	max. 1.7µm
Brightness C/2° (ISO 2470)	min. 87

Printing Surface Properties

ISO Brightness	90
CIE Whiteness D65/10° (ISO 11475).....	120
Surface smoothness (PPS)	1.0µm
Gloss 75° (ISO 8254-1).....	45%



The mark of
responsible forestry
FSC® C016680