

Oppboga Truecoat C2S

Multi-layer solid bleached board, double coated on both sides

SUB-STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m ²	μm pt	MD	CD	MD	CD
400	410		550	275	27	14
430*	460					
450	520		825	400	40	19
470*	540		875	475	42	23
500	600		1175	600	57	29
560*	660		1475	775	71	37
600	720		1950	1000	94	48
670*	830					

*Available on request, please contact our sales team.



White. Smooth. Vibrant

APPLICATIONS

Luxury packaging • high-end graphics

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

The multi-layer board structure allows for excellent conversion.

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)	±4%
Thickness (DIN ISO 534)	±4%
Bending stiffness (ISO 5629)	-15%
ISO Brightness C/2° (ISO 2470)	min. 92
Smoothness (ISO 8791-4)	max 1.4μm

Printing Surface Properties

ISO Brightness	95
CIE Whiteness D65/10° (ISO 11475)	135
Surface smoothness (PPS)	0.9μm
Gloss 75° (ISO 8254-1)	48%