

# Oppboga Truecoat™ C2S

Multi-layer solid bleached board, double coated on both sides

SUB-STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m <sup>2</sup>	µm	pt	MD	CD	MD
400	410	16	550	275	27	14
430*	460	18				
450	520	20	825	400	40	19
470*	540	21	875	475	42	23
500	600	24	1175	600	57	29
560*	660	26	1475	775	71	37
600	720	28	1950	1000	94	48
670*	830	33				

\*Available on request, please contact our sales team.



**White. Smooth. Vibrant.**

## APPLICATIONS

Luxury packaging • high-end graphics

## PRINTING

Offset printing • screen printing • large format digital printing

## CONVERSION

The multi-layer board structure allows for excellent conversion.

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

## ADDITIONAL INFORMATION

[www.oppboga.com](http://www.oppboga.com)

### Tolerances / Testing Standards

Grammage (DIN ISO 536) .....	±4%
Thickness (DIN ISO 534) .....	±4%
Bending stiffness (ISO 5629) .....	-15%
ISO Brightness C/2° (ISO 2470) .....	min. 92
Smoothness (ISO 8791-4) .....	max 1.4µm

### Printing Surface Properties

ISO Brightness .....	95
CIE Whiteness D65/10° (ISO 11475) .....	135
Surface smoothness (PPS) .....	0.9µm
Gloss 75° (ISO 8254-1) .....	48%