

Oppboga Truecoat™ RR

Multi-layer solid bleached board with a light surface coating on both sides

SUB-STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m ²	µm pt	MD	CD	MD	CD
400	410	16	550	275	27	14
430*	460	18				
450	520	20	825	400	40	19
470*	540	21	875	475	42	23
500	600	24	1175	600	57	29
560*	660	26	1475	775	71	37
600	720	28	1950	1000	94	48
670*	830	33				

*Available on request, please contact our sales team.



White. Smooth. Vibrant.

APPLICATIONS

Luxury packaging • high-end graphics

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

The multi-layer board structure allows for excellent conversion.

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)±4%
 Thickness (DIN ISO 534)±4%
 Bending stiffness (ISO 5629)-15%
 ISO Brightness C/2° (ISO 2470) min. 92
 Smoothness (ISO 8791-4) max 1.4µm

Printing Surface Properties

ISO Brightness95
 CIE Whiteness D65/10° (ISO 11475) 135
 Surface smoothness (PPS) 0.9µm



The mark of
responsible forestry
FSC® C016680